

# 20-1625 OPTICALLY CLEAR SILICONE POTTING AND ENCAPSULATING COMPOUND

## **DESCRIPTION:**

20-1625 is a low viscosity and easy to use 1:1 ratio silicone system. It is designed for applications that require clarity and protection from shock and vibration. 20-1625 provides good heat resistance and is flame retardant.

20-1625 is formulated without solvents or other toxic materials. It is therefore not regulated or considered hazardous for transportation.

## **FEATURES:**

- Easy 1:1 mix ratio
- Soft
- Excellent electrical properties
- Solvent free
- · Optically clear

## **BENEFITS:**

- Simple to use
- Low stress on components and vibration resistant
- Extends life of electronic assemblies
- No by-products released during cure and safe to handle
- Easy component identification

# **TYPICAL SPECIFICATIONS:**

Color

Resin (Part A)	Clear
Activator (Part B)	Clear
Viscosity, @ 25°C, cps	
Resin (Part A)	4,500
Activator (Part B)	4,000

Specific Gravity, @ 25°C

Resin (Part A) 0.98 Activator (Part B) 0.98

Working Time, 25°C 20 minutes
Refractive Index (liquid) 1.403 @ 589 nm
Spectral Transmission (cured) >95% @ 360-2100 nm

Spectral Transmission (cured) >95% @ 360-210 Hardness, Shore A 25 Thermal Conductivity, btu·in/hr·ft².°F 1.1

Coefficient of Thermal Expansion, per °C 27 x 10<sup>-5</sup> Volume Resistivity, ohm-cm, 25°C 1 x 10<sup>15</sup> Dielectric Constant @ 60 Hz 2.7 Dielectric Strength, V/mil 500

Operating Temperature, °C -55 to +200

## **CURE SCHEDULE**

at 25°C 3-4 hours at 60°C 60 minutes



#### **INSTRUCTIONS FOR USE:**

- 1. By weight or volume, mix 1 part base silicone to 1 part activator. Mix uniformly, scraping sides and bottom of mixing container. Do not whip air into mixture.
- 2. De-air by pulling vacuum on mixed material.

## **SUBSTRATE NOTES:**

Certain materials may inhibit the cure of this product. Materials that should be avoided include sulfur containing materials, nitrogen containing materials (i.e. amines) some silicones (tin cured), and butyl and chlorinated rubbers. If in doubt, a patch test should be done.

#### STORAGE:

When stored in the original, unopened container, in a dry location at 65° - 80°F, the 20-1625 has a shelf life of approximately twelve months.

## PACKAGING RECOMMENDATION:

Using the popular TriggerBond® cartridges will add convenience and reliability.

#### **AVAILABILITY:**

20-1625 is available in quart, gallon, five gallon pail, and 55 gallon drums. The silicone system is also available in the popular TriggerBond® 50ml, 200ml, and 400 ml cartridges.

#### **IMPORTANT:**

**EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS.** The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

06/23