

50-3150FRBK FLAME RETARDANT THERMALLY CONDUCTIVE EPOXY RESIN; UL 94 V-0 LISTED

DESCRIPTION:

50-3150FRBK offers excellent heat transfer, low shrinkage, and outstanding insulation properties. It is formulated to meet the stringent non-burning requirements of UL94 V-0.

50-3150FRBK with Catalyst 12, Catalyst 190, Catalyst 30 are listed with Underwriter's Laboratory for passing UL 94 V-0. For low mixed viscosity with no UL listing requirements Catalyst 150 is available.

50-3150FRBK with Catalyst 30 has a UL (746B) **Relative Temperature Index (RTI) rating of 130°C.**

50-3150FRBK with Catalyst 190 **passes NASA's outgassing requirements** per ASTM E595-07.

This system is an excellent choice for applications requiring high thermal conductivity and flame retardancy. Typical applications for 50-3150 FR include potting and encapsulating power supplies, transformers, electric motors, capacitors, batteries, coils, insulators, sensors, devices for intrinsic safety, etc.

TYPICAL PROPERTIES:

Viscosity, cps, 25°C, Resin	85,000
Mixed with Cat. 190	28,000
Mixed with Cat. 30	17,000
Mixed with Cat. 12	2,000
Mixed with Cat. 150	1,500
Color	Black
Hardness, Shore D	90
Operating Temp. Range, °C	-60 to +200
Specific Gravity, 25°C	1.6
Compressive Strength, psi	15,000
Linear Shrinkage, in/in	0.002
Tensile Strength, psi	9,850
Dielectric Strength, V/mil	485
Dielectric Constant, 60 Hz	5.6
Dissipation Factor, 60 Hz	0.015
Volume Resistivity, ohm-cm, 25°C	1.5 x 10 ¹⁵
Coefficient of Expansion, ppm/°C	14
Thermal Conductivity, W/m·°K	2.16



Heat Distortion, °C	155
Outgassing (with Cat. 190)	
%TML	0.50
%CVCM	0.01

INSTRUCTIONS FOR USE:

- A. With Catalyst 190 listed with UL 94 V-0 and passes NASA outgassing:
1. By weight, thoroughly mix 5 parts Catalyst 190 to 100 parts 50-3150FR resin.
 2. Degas, pour, and cure according to one of the following recommended cure schedules:
 - a) 25 °C 12-24 hours
 - b) 60 °C 1 hour
- B. With Catalyst 30 listed with UL 94 V-0 and RTI Rating of 130 °C:
1. By weight, thoroughly mix 10 parts Catalyst 30 to 100 parts 50-3150FR resin.
 2. Degas, pour, and cure according to one of the following recommended cure schedules:
 - a) 85 °C 3-4 hours
 - b) 100 °C 2-3 hours
- For optimum performance, an additional 2 hours at 185 °C is recommended.
- C. With Catalyst 12 listed with UL 94 V-0 Rating:
1. By weight, thoroughly mix 12 parts Catalyst 12 to 100 parts 50-3150 FR resin.
 2. Degas, pour, and cure according to one of the following recommended cure schedules:
 - a) 25 °C 48 hours
 - b) 65 °C 4-6 hours
- D. With Catalyst 150 (not UL listed):
1. By weight, thoroughly mix 17 parts Catalyst 150 to 100 parts 50-3150 FR resin.
 2. Degas, pour, and cure according to one of the following recommended cure schedules:
 - a) 25 °C 24 hours
 - b) 35-40 °C 2-3 hours

STORAGE & HANDLING:

The expected shelf life is 12 months in original unopened containers.
Please read Safety Data Sheet before using this or any other chemical.

AVAILABILITY:

50-3150FRBK is available in quarts, gallons, and 5-gallon pails.

IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

03/24